



Ultra matt topcoat for levelled industrial looking floors

- Final treatment of cement-based levelled floors
- Interior application in dry rooms
- Ultra matt transparent look
- Enhances surface strength
- Ready for use and easy to apply
- High wear and water resistance
- High waterproofing

Product

1-component water-based acrylic and polyurethane dispersion

Coverage

0.10.- 0.15 l/m² pr coat
Total consumption for 3 coats approx. 0.35 l/m²

Packaging

2.5 l and 10 l container

Surface preparation

The surface should be dimensionally stable, dry, fully cured and dust-free
Any laitance left on the surface should be removed by grinding before surface treatment with Alfix TopCoat Design is applied.

For further information, please consult our Technical Services Dept.

Application

Always shake container well before use to dissolve any precipitate

For highly absorbent surfaces, apply first coat of Alfix TopCoat diluted with up to 10% clean water. Apply by short-haired paint roller for even and full coverage leaving no visible puddles.
Leave to dry for at least 3 hours before applying second coat Alfix TopCoat Design by short-haired paint roller.

Leave to dry for another 3 hours to dry or await the following day until applying the third and final coat of Alfix TopCoat Design.

Observe that temperature at ceiling, floor and product should range from +15°C to +25°C.

Min. drying time at +20°C: 3 hours between each application.

Allow floor to dry for at least 24 hours at +20°C before taking into use.

Cleaning

Clean residues from tools with water before the dispersion sets. Once dried, Alfix TopCoat Design can be removed mechanically.

Daily maintenance

The floor surface should be maintained as a lacquered or oil-treated floor.

For washing, Alfix Gulvpleje or a similar detergent with the same specifications is recommended.

NB!

Alfix TopCoat Design is recommended for floors in living spaces or other floor areas where the load on the floor is comparable with the load in living spaces.


For floor areas with a greater load than in living spaces, more frequent maintenance should be expected. Use of an underlay below office chairs with castors is recommended.

For chairs and other objects that are often pulled across the floor, we recommend fitting felt pads or similar below the chair legs etc.

We recommend placing mats on the floor surface by entrances.

Spillages on the floor should be wiped up before drying.

For further information, please contact our Technical-Service department.



Test

Low emission, GEV-EMICODE EC1 - test defined by the German institute Gemeinschaft Emissionskontrollierte Verlegestoffe.

Technical enquiries

Product info on:

Alfix PlaneMix

Alfix PlaneMix Safety Datasheet /COSH

For further information, please consult our Technical Services Dept

For latest update of this product info, visit www.alfix.com

Technical data

Working temperature:	Room, floor, and TopCoat: Min. +15°C / Max. +25°C
Density	1.0 kg/litre
Gloss/sheen	(20°/60°/85°) 0.5./2.4./ 1.9
Drying time	24 hours at +20°C
Shelf life	Min. 12 months in unopened container. Store at temperatures ranging from +5°C to max. +30°C