






































TECHNICAL CHARACTERISTICS

PURLINE organic flooring | wineo 1200 to glue

Permanently elastic polyurethane flooring according to EN 16776
Without the addition of chlorin, without plasticisers or solvents.

wineo

	wood XS	stone XS	wood XL V4	stone XL		
Format	480 x 80 mm	480 x 80 mm	1500 x 250 mm	1000 x 500 mm		
Product thickness	2.2 mm	2.2 mm	2.2 mm	2.2 mm		
Weight	3.0 kg/m ²	3.0 kg/m ²	3.0 kg/m ²	3.0 kg/m ²		
Planks / m² per box	45 / 1.73 m ²	45 / 1.73 m ²	14 / 5.25 m ²	12 / 6.00 m ²		
Boxes / m² per pallet	144 / 249.12 m ²	144 / 249.12 m ²	56 / 294.00 m ²	50 / 300.00 m ²		
Guarantee	Life Time Guarantee for private use according to Windmüller warranty conditions – www.wineo.de					
Classification					Product composition	
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage			1	Top element • PU-top layer with surface structure • decor paper • stabilisation
	Utilization class 33 EN ISO 10874	Commercial sector with heavy usage				
	Utilization class 42 EN ISO 10874	Light industry sector with moderate usage				
	Scratch resistance EN 16776, annex A	Utilization class 33 ≥ 6 N Utilization class 42 ≥ 7 N			2	Base layer ecuran high performance composite
	Anti slip category DIN 51130	R 9			3	Backing Integrated Fleece TEC-System
	Staining and chemical resistance EN ISO 26987	Very good resistance according to the concentration and residence time				wood XL V4 joint lacquered 
	Light fastness EN ISO 105-B02	~ 7				
	Residual indentation EN ISO 24343-1	≤ 0.10 mm				
	Effect of a furniture leg EN 424	Foot type 2 – no visible change				
	Castor chair test EN ISO 4918	25000 revolutions no damage with rolls type W				
	Thermal resistance ISO 8302	0.01 (m ² K)/W				
	Impact sound reduction EN ISO 10140	in test				
	Dimension stability EN ISO 23999	≤ 0.15 %				
	Flexural behaviour EN ISO 24344	≥ 20 mm				
	REACH	free from SVHC substances ≥ 0.1 %				
	Disposal	Private: possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203				
		Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf				
DOP: 2001010 EN 14041:2004 / AC2006 1658						
		Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)				
						
						
						
						
						

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperatur of 27 °C.
- Cleaning and care: See separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.